

# REUSCHE GLASS STAINERS COLORS

## QUALITY PRODUCTS SINCE 1906

- 01 8183MB Bistre Black
- 02 1058A Soft Black
- 03 1059 Stencil Black
- 04 1063 Tracing Black 61

- 05 1065 Universal Black
- 06 1066 Vinegar Trace Black
- 07 1109 Ancient Brown
- 08 1110 Bistre Brown
- 09 1134 Tracing Brown 1
- 10 1139 Umber Brown
- 11 1139D Umber Brown-Grey
- 12 1139E Umber Brown-Sepia
- 13 1139F Umber Brown-Red
- 14 1140A Vinegar Trg Brown
- 15 1203A Black Green Dark
- 16 1205A Black Green Gris
- 17 1220A Grey Green

- 18 1220C Grey Green Matting
- 19 1333 Red for Flesh
- 20 DE401 Tracing Black
- 21 DE402 Bistre Brown
- 22 DE403 Umber Brown
- 23 DE404 Ancient Brown
- 24 DE405 Ancient Brown
- 25 DE458 Tracing Black Best
- 26 DF476 Flesh Red
- 27 8212MB White
- 28 7852MB Strong Blue
- 29 7854MB Pastel Blue
- 30 7865MB Teal Blue

- 31 7869MB Blue Green
- 32 7870MB Dark Green
- 33 7871MB Soft Yellow
- 34 7872MB Lemon Yellow
- 35 7875MB Orange
- 36 7882MB Blood Red
- 37 7883MB Pink
- 38 7885MB Apple Green
- 39 4776MB G/S Satin Etch
- 40 1400GS Obscuring White
- 41 1402A Matting White
- 42 D201581 White
- 43 D211824 Yellow Red

- 44 D211827 Blue Red
- 45 D211831 Maroon
- 46 D232782 Green-Yellow
- 47 D232786 Orange Yellow
- 48 D232792 Gold-Yellow
- 49 D242013 Black
- 50 D252174 Green
- 51 D261935 Chrome Green
- 52 D261939 Blue-Green
- 53 D273889 Green-Blue
- 54 D273893 Red Blue
- 55 D273908 Dark Blue
- 56 D281097 Orange

- 57 D293355 Red Brown
- 58 D293360 Brown
- 59 D293363 Buff
- 60 D293371 Dark Brown
- 61 D293376 Dark Brown
- 62 D21877 Violet 2B151
- 63 D211513 Ruby 2776
- 64 D221620 Violet 2803
- 65 D22891 Carmine 2777
- 66 D22932 Carmine
- 67 D231176 Amber L349
- 68 D232255 Yellow 2865
- 69 D24418 Smoke Grey


- 70 D25822 Chartreuse
- 71 D261676 Green V554
- 72 D26169 Green D0541
- 73 D26346 Green
- 74 D26354 Turquoise Green
- 75 D26762 Turquoise
- 76 D273359 Blue 2867
- 77 D27778 Blue
- 78 D29400 Trans Brown
- 79 1061 Tracing Black #1
- 80 1081B Flash Blue Trans
- 81 1090 Trans Blue #1
- 82 1091 Trans Blue #2

- 83 1115A Dark Brown
- 84 1118B Dark Brown Trans
- 85 1129A Red Brown Trans
- 86 1298A Ruby Trans
- 87 1326A Flesh Tint Trans
- 88 7106MB Rouge
- 89 D2070 Satin White
- 90 D2342 Matt Black
- 91 D2617 White
- 92 D2788 Satin Etch
- 93 D2840 Intense Black
- 94 D2862 Canary Yellow
- 95 D2863 Jonquil Yellow

- 96 D2864 Dark Orange
- 97 D2866 Empire Green
- 98 D2868 Dark Blue
- 99 D2869 Holland Blue
- 100 D2870 Resolute Blue
- 101 D2872 Blood Red
- 102 D2873 Bright Red
- 103 D2875 Dark Brown Trans.
- 104 D2876 Art Brown
- 105 D2877 Black
- 106 D2881 Leaf Green
- 107 D2883 Chrome Green
- 108 D20129 Matt White

- 109 D2879 Soft Flux
- 110 DX603 White
- 111 DX660 White
- 111A D20511 White
- 111B DX692 White
- 112 1382 Orange 1
- 113 1383 Orange 2
- 114 1384 Yellow 3
- 115 1388 Orange Intense
- 116 D292465 Amber Stain H465
- 117 50R001 Clear Glaze
- 118 51R001 Snow White
- 119 51R002 True White

# REUSCHE GLASS STAINERS COLORS



## VITREOUS PAINTS & STAINS:

Vitreous paint is a mixture of ground glass and a pigment oxide. These superior glass stains and paints from Reusche are offered in 1oz. (28.3 gm) packets, containing powdered colors which must be mixed with water and gum arabic or other mixing agents before application to glass and subsequent kiln firing. 1 oz. covers 300 square inches.

## KIT COLORS:

Firing temperature: 1200°F-1250°F (648°C-676°C). Refills for Reusche kits.

## GLASS STAINERS COLORS:

Firing temperatures 1200°F-1250°F (648°C-676°C). Not bright transparent stains, these are basic paints for painting on glass. Opaque colors are limited to blacks, browns, flesh, red & grey-greens.

## SILVER STAINS:

Firing temperature: 1050°F-1080°F (565°C-586°C). Contains silver nitrate and gamboge gum; available in the range of intensities from pale yellow to orange intense.

## TRANSPARENT COLORS:

Firing temperature: 1050°F-1080°F (565°C-586°C). Enamels are vitreous paints & become transparent when fired at lower temperatures. Not as durable as glass stainers weather resistant colors.

## GOLD BASE TRANSPARENT COLORS:

Firing temperature: 1050°F-1080°F (565°C-586°C).

NOTE: Do not apply to tin side of floating glass.

## BENDABLE BENDING COLORS:

Firing temperature: 1200°F-1300°F (626°C-704°C). Unique because they liquefy before the glass reaches bending stage. Opaque colors remain fluid without running through the glass bending or slumping period. They do not burn out or change color (as is common with some transparent colors, particularly cadmium or selenium colors: red, orange, maroon, etc). Bending colors are stable through the 1160°F-1300°F firing range. May be fired while glass is flat. Colors can be lightened by adding White (Cat. No D201581). Adding other colors will achieve entirely different colors.

**GUM ARABIC:** A vehicle used to mix with vitreous paints for flow and bind.